

**E314**

M	~DIN <b>371</b>	6H		1.5XD	HSS-E-PM	<b>C</b> 2-3			
---	--------------------	----	---	-------	----------	-----------------	---	---	---

**E316**

M	DIN <b>376</b>	6H		1.5XD	HSS-E-PM	<b>C</b> 2-3			
---	-------------------	----	---	-------	----------	-----------------	---	---	---

- M 机用丝锥 CoroTap™ P 螺旋槽 15°
- M Tarauls machine CoroTap™ P Goujure hélicoïdal 15°
- M Maschinen-Gewindebohrer CoroTap™ P, 15° Spirale
- M Macho Máquina CoroTap™ P Canal Helicoidal 15°
- M Machos de máquina CoroTap™ P Estrías helicoidales a 15°
- M Machine CoroTap™ P Spiral Flute 15°



CoroTap™ 300 



<b>P</b>	
P 1	---
P 2	<b>9-20</b>
P 3	<b>9-20</b>
P 4	---
P 5	<b>9-20</b>
Vc[m/min]	

Din EN 42CrMo4/ 1.7225/ SS2244 MC-code: P2.5.Z.HT 311HB	P2	↓ 1.5xD			Vc [m/min]		N [rpm]	Vf [mm/min]
			M	TP				
			M3	0.5	21	2206	1103.0	
M4	0.7	21	1655	1158.5				
M5	0.8	21	1324	1059.2				
M6	1	21	1103	1103.0				
M8	1.25	21	827	1033.8				
M10	1.5	21	662	993.0				
M12	1.75	21	552	966.0				
M16	2	18	363	726.0				
M20	2.5	17	263	657.5				

Toolox 44 MC-code: P2.5.Z.HT 415 HB	P2	↓ 1.5xD			Vc [m/min]		N [rpm]	Vf [mm/min]
			M	TP				
			M3	0.5	13	1428	714.0	
M4	0.7	13	1071	749.7				
M5	0.8	13	857	685.6				
M6	1	13	714	714.0				
M8	1.25	13	535	668.8				
M10	1.5	13	428	642.0				
M12	1.75	13	357	624.8				
M16	2	12	235	470.0				
M20	2.5	11	170	425.0				

# 材料对照表/Tableaux de correspondance matériau/ Quererverweistabellen (Material)/Tabelas de Referência Cruzada de Materiais/Tablas de referencias cruzadas de materiales/Material Cross Reference Tables

//Norme et Pays/région//Standard & Land/Region//Padrão & País/Região//Estándar y país/región//Standard & Country/Region												
ISO	MC-code	Dormer AMG	Europe DIN EN	Germany W.-nr	UK BS	EN	Sweden SS	USA AISI/SAE/ASTM	France AFNOR	Italy UNI	Spain UNE	Japan JIS
<b>P 非合金钢/Aciers non alliés/Unlegierter Stahl/Aços sem liga/Acero no aleado/ Unalloyed steels</b>												
P1.1.Z.AN	1.2	S235JR G2	1.0038	4360 40 C			1311	A570.36	E 24-2 Ne			STKM 12A;C
P1.1.Z.AN	1.2	S235J2 G3	1.0116	4360 40 B			1312	A573-81 65	E 24-U	Fe37-3		
P1.1.Z.AN	1.2	C15	1.0401	080M15	-		1350	1015	CC12	C15C16	F.111	-
P1.1.Z.AN	1.2	C22	1.0402	050A20	2C/2D		1450	1020	CC20	C20C21	F.112	-
P1.1.Z.AN	1.2	C15E	1.1141	080M15	32C		1370	1015	XC12	C16	C15K	S15C
P1.1.Z.AN	1.2	C25E	1.1158	-	-		-	1025	-	-	-	S25C
P1.1.Z.AN	1.2	S380N	1.8900	4360 55 E			2145	A572-60	-	FeE390KG		
P1.1.Z.AN	1.3	17MnV7	1.0870	4360 55 E			2142	A572-60	NFA 35-501 E 36	-	-	
P1.1.Z.AN	1.3	55Si7	1.0904	250A53	45		2085	9255	55S7	55Si8	56Si7	-
P1.1.Z.HT	1.3	-	-	-	-		2090	9255	55S7	-	-	-
P1.2.Z.AN	1.2	S275J2G3	1.0144	4360 43C			1412	A573-81	E 28-3	-	-	SM 400A;B;C
P1.2.Z.AN	1.2	S355J2G3+C2	1.0570	4360 50B			2132	-	E36-3	Fe52BFN/ Fe52CFN	-	SM490A;B;C; YA;YB
P1.2.Z.AN	1.2	S355J2G3	1.0841	150 M 19			2172	5120	20 MC 5	Fe52	F-431	-
P1.2.Z.AN	1.3	C35	1.0501	060A35	-		1550	1035	CC35	C35	F.113	-
P1.2.Z.AN	1.3	C45	1.0503	080M46	-		1650	1045	CC45	C45	F.114	-
P1.2.Z.AN	1.3	40Mn4	1.1157	150M36	15		-	1039	35M5	-	-	-
P1.2.Z.AN	1.3	36Mn5	1.1167	-	-		2120	1335	40M5	-	36Mn5	SMn438(H)
P1.2.Z.AN	1.3	28Mn6	1.1170	150M28	14A		-	1330	20M5	C28Mn	-	SCMn1
P1.2.Z.AN	1.3	C35G	1.1183	060A35	-		1572	1035	XC38TS	C36	-	S35C
P1.2.Z.AN	1.3	C45E	1.1191	080M46	-		1672	1045	XC42	C45	C45K	S45C
P1.2.Z.AN	1.3	C53G	1.1213	060A52	-		1674	1050	XC48TS	C53	-	S50C
P1.2.Z.AN	1.3	C55	1.0535	070M55	-		1655	1055	-	C55	-	-
P1.2.Z.AN	1.3	C55E	1.1203	070M55	-		-	1055	XC55	C50	C55K	S55C
P1.3.Z.AN	1.3	C60E	1.0601	080A62	43D		-	1060	CC55	C60	-	-
P1.3.Z.AN	1.3	C60E	1.1221	080A62	43D		1678	1060	XC60	C60	-	S58C
P1.3.Z.AN	1.3	C101E	1.1274	060 A 96			1870	1095	XC 100	-	F-5117	-
P1.3.Z.AN	1.3	S340 MGC	1.0961	-	-		-	9262	60SC7	60SiCr8	60SiCr8	-
P1.3.Z.AN	1.4	C101u	1.1545	BW 1A			1880	W 1	Y105	C36KU	F-5118	SK 3
P1.3.Z.AN	1.4	C105W1	-	BW2	-		2900	W210	Y120	C120KU	F.515	SUP4
P1.4.Z.AN	1.2	11SMn30	1.0715	230M07	-		1912	1213	S250	CF9SMn28	11SMn28	SUM22
P1.4.Z.AN	1.2	11SMnPb30	1.0718	-	-		1914	12L13	S250Pb	CF9SMnPb28	11SMnPb28	SUM22L
P1.4.Z.AN	1.2	10SPb20	1.0722	-	-		-	-	10PbF2	CF10SPb20	10SPb20	-
P1.4.Z.AN	1.2	11SMn37	1.0736	240M07	1B		-	1215	S 300	CF9SMn36	12SMn35	-
P1.4.Z.AN	1.2	11SMnPb37	1.0737	-	-		1926	12L14	S300Pb	CF9SMnPb36	12SMnP35	-
P1.4.Z.AN	1.2	35S20	1.0726	212M36	8M		1957	1140	35MF4	-	F210G	-
P1.5.C.UT	1.2	GC16E	1.1142	030A04W	1A		1325	1115	-	-	-	-
<b>低合金钢/Aciers faiblement alliés/Niedriglegierter Stahl/Aços baixa-liga/ Acero de aleación baja/Low-alloyed steels</b>												
P2.1.Z.AN	1.3	16MnCr5	1.7139	-	-		2127	-	-	-	-	-
P2.1.Z.AN	1.4-1.6	16Mo3	1.5415	1501-240	-		2912	A204Gr.A	15D3	16Mo3KW	16Mo3	-
P2.1.Z.AN	1.4-1.6	14Ni6	1.5622	-	-		-	A350LF5	16N6	14Ni6	15Ni6	-
P2.1.Z.AN	1.4-1.6	21NiCrMo2	1.6523	805M20	362		2506	8620	20NCD2	20NiCrMo2	20NiCrMo2	SNCM220(H)
P2.1.Z.AN	1.4-1.6	17CrNiMo6	1.6587	820A16	-		-	-	18NCD6	-	14NiCrMo13	-
P2.1.Z.AN	1.4-1.6	15Cr3	1.7015	523M15	-		-	5015	12C3	-	-	SCr415(H)
P2.1.Z.AN	1.4-1.6	55Cr3	1.7176	527A60	48		-	5155	55C3	-	-	SUP9(A)
P2.1.Z.AN	1.4-1.6	15CrMo5	1.7262	2127	-		2216	-	12CD4	-	12CrMo4	SCM415(H)
P2.1.Z.AN	1.4-1.6	13CrMo4-5	1.7335	1501-620Gr27	-		-	A182 F11;F12	15CD3.5	14CrMo45	14CrMo45	-
P2.1.Z.AN	1.4-1.6	10CrMo9 10	1.7380	1501-622Gr. 31;45	-		2218	A182 F.22	12CD9, 10	12CrMo9, 10	TU.H	-
P2.1.Z.AN	1.4-1.6	14MoV6 3	1.7715	1503-660-440	-		-	-	-	-	13MoCrV6	-
P2.1.Z.AN	1.4-1.6	50CoMo4	1.7228	823M30	33		2512	-	-	653M31	-	-
P2.1.Z.AN	1.4-1.6	14NiCrMo134	1.6657	832M13	36C		-	-	-	15NiCrMo13	14NiCrMo131	-
P2.1.Z.AN	1.4-1.6	16Mo5	1.5423	1503-245-420	-		-	4520	-	16Mo5	16Mo5	-
P2.1.Z.AN	1.4-1.6	22Mo4	1.5419	605A32	-		2108	8620	25CD4	-	F520.S	-
P2.1.Z.AN/P2.5.Z.HT	1.4-1.6	25CrMo4	1.7218	1717CDS110	-		2225	4130	16MC5	25CrMo4(KB)	AM26CrMo4	SCM420; SCM430
P2.1.Z.AN/P2.5.Z.HT	1.4-1.6	16MnCr5	1.7131	(527M20)	-		2511	5115	35CD4	16MnCr5	16MnCr5	-
P2.1.Z.AN/P2.5.Z.HT	1.4-1.6	34CrMo4	1.7220	708A37	19B		2234	4137;4135	42CD4TS	35CrMo4	34CrMo4	SCM432; SCCRM3
P2.1.Z.AN/P2.5.Z.HT	1.4-1.6	41CrMo4	1.7223	708M40	19A		2244	4140;4142	42CD4	41CrMo4	42CrMo4	SCM 440
P2.1.Z.AN/P2.5.Z.HT	1.4-1.6	42CrMo4	1.7225	708M40	19A		2244	4140	30 CD 12	42CrMo4	42CrMo4	SCM440(H)
P2.2.Z.AN	1.4-1.6	31CrMo12	1.8515	722 M 24			2240	-	-	30CrMo12	F-1712	-
P2.2.Z.AN	1.4-1.6	39CrMoV13 9	1.8523	897M39	40C		-	-	-	36CrMoV12	-	-
P2.2.Z.AN	1.4-1.6	41CrS4	1.7039	524A14	-		2092	L1	-	105WCR 5	-	-
P2.2.Z.AN	1.4-1.6	45WCrV7	1.2542	BS1	-		2710	S1	-	45WCrV8KU	45WCrSi8	-
P2.2.Z.AN	1.4-1.6	40NiCrMo8-4	1.6562	311-Type 7	-		-	8740	-	40NiCrMo2(KB)	40NiCrMo2	SNCM240
P2.2.Z.AN	1.4-1.6	42Cr4	1.7045	-	-		2245	5140	-	-	42Cr4	SCr440
P2.2.Z.AN	1.4-1.6	31NiCrMo14	1.5755	830 M 31			2534	-	55NCV6	-	F-1270	-
P2.2.Z.AN	1.6	50NiCr13	1.2721	-	-		2550	L6	40NCD3	-	F-528	-

钢/Acier/Stahl/Aços/Acero/Steel

